

**SECTION 07 14 16  
FLUID APPLIED WATERPROOFING (WATER BASED)  
OVER GRANULAR MODIFIED**

**PART 1 GENERAL**

**1.1 SECTION INCLUDES**

- A. Fluid applied flexible acrylic waterproofing system over Granular Modified.

**1.2 RELATED SECTIONS**

- A. Section 07 22 16      Roof Deck Insulation Board
- B. Section 03 30 00      Cast in place Concrete

**1.3 REFERENCES**

- A. ASTM D2370      Test Method for Tensile Properties of Plastics.
- B. ASTM D1204      Test Method for Linear Dimensional changes of Non-rigid Thermoplastic Sheetting or Film at Elevated Temperature.
- C. ASTM G26      Practice for Operating Light Exposure Apparatus (Xenon Arc Type) With and Without Water for Exposure of Non Metallic Surfaces.
- D. ASTM E96      Water Vapor Transmission of Materials.
- E. ASTM E 108      Test Methods for Fire Test of Roof Coverings.
- F. FM 4470      Wind Uplift Resistance.

**1.4 SUBMITTALS**

- A. Shop Drawings: Indicate special joint or termination conditions and conditions of interface with other materials.
- B. Product Data: Provide data for material description, physical properties, recommended storage conditions, shelf life, precautions, flexible flashings, and joint and crack sealants, with temperature range for application of waterproofing membrane.
- C. Manufacturer's Installation Instructions: Indicate special procedures and perimeter conditions requiring special attention.
- D. Test Data: Provide documentation supporting tests referred to under item 1.3.

**1.5 QUALIFICATIONS**

- A. Applicator: Company specializing in performing the work of this section approved by manufacturer.
- B. Manufacturer: Company shall have been manufacturing specified products for a minimum of 15 years.

**1.6 REGULATORY REQUIREMENTS**

- A. Products: V.O.C. Requirements shall be less than 90 grams/liter.

**1.7 DELIVERY, STORAGE, AND HANDLING**

- A. Deliver materials to site in manufacturer's unopened and undamaged containers bearing the following information:
  - 1. Name of manufacturer
  - 2. Name of contents and products code
  - 3. Net volume of contents
  - 4. Lot or batch number
  - 5. Storage temperature limits
  - 6. Shelf life expiration date
  - 7. Mixing instructions and proportions of contents
  - 8. Safety information and instructions
- B. Store and protect materials from damage and weather in accordance with manufacturer's instructions.
- C. Store materials at temperatures between 40°F and 90°F. Keep out of direct sunlight.
- D. Support stored material containers on pallets and cover with tarpaulin tied to bottom of pallets.



## PART 3 EXECUTION

### 3.1 EXAMINATION

- A. Verify substrate surfaces are durable, free of frozen matter, dampness, loose particles, cracks, pits, projections or foreign matter detrimental to adhesion or application of waterproofing system.
- B. Verify that substrate surfaces are smooth and not detrimental to full contact bond of waterproofing materials.
- C. Verify that roof surface has positive drainage.

### 3.2 PREPARATION

- A. Protect adjacent surfaces not designated to receive waterproofing.
- B. Clean and prepare surfaces to receive waterproofing by removing all loose and flaking particles, grease, dirt and laitance.
- C. Do not apply waterproofing to surfaces unacceptable to manufacturer.
- D. Seal cracks and joints with sealant materials using depth to width ratio as recommended by sealant manufacturer.

### 3.3 APPLICATION

- A. Apply accessory primer(s) as required. Allow to dry.
- B. Apply 3/8" triangular bead of Adhesive Sealant at internal corners.
- C. Apply Base Coat, Flashing Fabric and Saturation Coat over board joints, cracks, flashings and non-working joints at 27 sq.ft. per gallon. Allow to dry.
- D. Optional: apply primed metal drip edge at perimeter, adhering into place with Adhesive Sealant.
- E. Apply Base Coat, Field Fabric and Saturation Coat at 27 sq. ft. per gallon over the entire area. Overlap adjacent runs of fabric 3" minimum. Allow to dry.
- F. Apply two coats of Finish Coat over the entire area at 140 sq. ft. per gallon per coat. Allow to dry between coats.
- G. Waterproofing system should be a minimum of 45 mils total cured thickness.

### 3.4 CLEANING

- A. Immediately clean adjacent areas not scheduled to receive waterproofing in accordance with manufacturer's recommendations.

### 3.5 PROTECTION OF FINISHED WORK

- A. Protect finished waterproofing from weather until cured.

END OF SECTION

**IMPORTANT NOTE:** Always check our website, [www.sealoflex.com](http://www.sealoflex.com) to determine if the printed literature you are reading is the most current version available.