

Commercial Product Data Sheet

Product Description

CT FibreSeal is a fiber-reinforced, single component SEBS base coating. It is a tough, flexible material which is used in conjunction with Sealoflex CT Top to form a fully adhered, monolithic membrane with good ponding water resistance.

Product Uses

- A substitute for CT Pink/Fabric/CT Pink in awkward or difficult to reach areas

Advantages

- Conforms to odd-shaped areas
- Highly flexible
- Resists ponding water
- Fast curing and may be applied at low temperatures
- Excellent low temperature flexibility
- Adheres to most roof or wall substrates
- Acid and alkali resistant

Colors

Pink

Packaging

5-gallon metal containers

Coverage Rates and Application

CT FibreSeal must be applied by spray when used over large areas. It cannot be brushed or rolled. For spray applications, contact the Sealoflex Technical Department. For smaller detail flashings and repairs, CT FibreSeal may be applied by brush. Apply one coat of CT FibreSeal at 25 sq. ft./gallon over prepared surface and allow to dry. Then apply two coats of Sealoflex CT Top at 70 sq. ft./gallon, total for both coats. Contact the Sealoflex Department for guidance.

Storage

Product shelf life is 12 months from date on container. Shelf life will be reduced if product is stored at temperatures above 77°F (25°C). Store indoors in a closed container in a well-ventilated, cool, dry area away from heat, open fire, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Materials stored on the job site during application should be kept on a pallet in a shaded, well-ventilated area. In unshaded areas, materials should be covered with a white, reflective tarp in a manner that allows air circulation beneath the tarp.

Instructions for Use

Surface Preparation

Surfaces must be clean and free of dust, loosely adhering particles, oil, grease, algae, mildew or fungal growth. Thoroughly stir the product before use. When using a mechanical mixer, do not over agitate. Over agitating will add air into the product, creating bubbles. After mixing, allow product to sit 5-10 minutes to allow trapped air to evacuate container to protect against product pinholes when applied. Sealoflex CT products can be applied when the substrate temperature is between 32°F (0°C) and 130°F (55°C). Discontinue resin application when the substrate temperature is outside the ranges listed above. Provide adequate shade over the substrate area both prior to and during application as necessary to maintain substrate surfaces below 130°F (55°C).

Priming

Refer to the Sealoflex Primer Chart.

Cleaning

Sealoflex CT can be dissolved with naphtha or mineral spirits.

Important Notes

- Determine if a primer is needed, and/or which primer is best for the application. Refer to the Pull Test Procedure on back of the Primer Chart.
- Prior to application of each coat of Sealoflex CT products, always ensure the surface is completely dry. Application of CT Products on damp or wet surfaces will result in blistering.
- If metal pan is used for concrete form, the metal must be vented. If between-slab membrane exists, surface breather vents are required. (Number of vents to be determined by others.)
- When applying the Sealoflex CT System on mechanically fastened EPDM, prepare the surface as follows: Apply EPDM Primer, allow to dry. Apply a generous coat of Sealoflex Pink (Water-Based) and allow to dry. A second option would be to apply EP1 Primer over the EPDM. The surface is now ready to accept the full Sealoflex CT System.
- Do not leave CT FibreSeal exposed. It must be covered with CT Top.

CT FibreSeal

Precautions

Read the MSDS on Sealoflex CT carefully before application. Avoid contact with eyes and skin. If eyes become contaminated flush with water for at least 15 minutes. If ingested do not induce vomiting and seek

medical attention immediately. Use only in well ventilated areas and avoid inhaling vapors. Avoid contact with static electricity, contact with sparks, open flame, motors and heat as Sealoflex CT is **FLAMMABLE**.

Physical and Mechanical Properties

Property (as Manufactured)	Value
Drying Time (Touch Dry)	1 hour at 77°F and 50% RH
Full Cure	7 days
Total System Thickness	40 mils dft
System Weight	0.30 lb./sq.ft.
Water Vapor Transmission Rate (ASTM E96)	6.3×10^{-3} grains/ft ² /hr at 45 mils dft
Elongation (ASTM D412)	61% (reinforced) 600% (unreinforced)
Tensile Strength (ASTM D412)	3,109 psi (Reinforced)

Ed. July 2016